


STRONGWELL[®]

CORROSION RESISTANCE GUIDE

INDUSTRIAL PRODUCTS





The cover photo shows severe, short-term corrosive effects of 37% sulfuric acid on various materials. All bar samples originally measured 6" long x 1/4" thick x 1/2" wide. Products depicted from left to right are carbon steel, EXTREN® Series 625, aluminum and EXTREN® Series 525. The steel base has deteriorated significantly below the solution line and incurred atmospheric corrosion. The aluminum also deteriorated and developed corrosive aluminum sulfite deposits. Both EXTREN® samples were not affected by the sulfuric acid solution.

Strongwell Corrosion Resistance Guide

The Resin Selection Guide for Strongwell Industrial Product Lines:

EXTREN®
FIBERGLASS STRUCTURAL SHAPES

DURA DEK®
HIGH STRENGTH GRATING

DURA GRATE®
MOLDED FIBERGLASS GRATING

DURA GRID®
CUSTOM FIBERGLASS GRIDS AND GRATING

FIBRE BOLT®
FIBERGLASS STUD AND NUT SYSTEM

DURA SHIELD®
FIBERGLASS FOAM CORE BUILDING PANELS

FIBERGLASS STRUCTURES
CUSTOM ENGINEERING AND FABRICATION

SAF RAIL™
FIBERGLASS HANDRAIL SYSTEM

SAF PLATE®
FIBERGLASS GRITTED PLATE

SAF PLANK®
FIBERGLASS PLANK SYSTEM

COMPOSOLITE®
FIBERGLASS BUILDING PANEL SYSTEM

NOTE: Information in this Corrosion Guide is specifically intended for the products manufactured by Strongwell and may have little correspondence to other pultruded or molded products.

*COMPOSOLITE® is a registered trademark of Maunsell Structural Plastics, Ltd. and used by Strongwell Corporation pursuant to license.



How To Use This Guide

Strongwell believes the information and recommendations herein to be accurate and reliable. Any questionable application should be preceded by a small sample or prototype evaluation in the actual chemical environment. Corrosive conditions not specifically discussed in this guide (including lower concentrations than those tested) should be referenced to Strongwell's Customer Service Department for an evaluation of the individual situation.

The specific recommendations in this Corrosion Guide are for immersion applications where good fabrication procedures have been followed. The pH of the solution can be used as an approximate indication of corrosion performance. A pH > 7.0 is caustic and will typically require a vinyl ester composite for immersion applications.

Special Considerations:

- DURAGRATE® - Corrosion resistance data for polyester resins is applicable only to the PP, premium (isophthalic) polyester resin system. The general purpose orthothalic polyester resin system (GP) is only recommended for corrosion situations such as salt water or mild wastewater and is not listed in this guide. Other corrosion chemicals will be reviewed individually for GP resin.
- DURASHIELD® - The cut ends must be sealed with an epoxy system for polyester and a vinyl ester system for the vinyl ester DURASHIELD® such that there is no possibility of chemical intrusion.
- Fiberglass Structures - The standard components of Strongwell FIBERGLASS STRUCTURES are shown in this *Corrosion Resistance Guide*. Fabrication procedures similar to those in Strongwell's *EXTREN® Fabrication and Repair Manual* should be followed to obtain the corrosion resistance stated in this guide.
- A spill/splash application can be considered separately if the spill/splash can be neutralized within one (1) hour.

The following definitions will aid readers using this Guide:

R.T.	Room Temperature ($\leq 100^{\circ}\text{F}$)
TP	Thermoplastic
R	Resistant
NR	Not Resistant
C	Concern (Indicates data is inconclusive. Customer is advised to confirm the corrosion resistance in their applications with pre-shipment sample.)
EXTREN® 500/525	Isophthalic Polyester
EXTREN® 625	Vinyl Ester
DURAGRATE®	
VE	Vinyl Ester
PP	Isophthalic Polyester (Premium Polyester)
GP	Orthothalic Polyester (General Purpose)*

*Not referred to in this *Corrosion Resistance Guide*

Note: Temperature data is not necessarily the maximum service temperature; it is the upper temperature at which a resin has been tested, used or evaluated. Other temperatures can be reviewed separately.

CHEMICAL ENVIRONMENT	VINYL ESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	VINYL ESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 160°F	POLYESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	POLYESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 150°F
A				
Acetic Acid 0-25%	R	R	R	R
Acetic Acid 25-50%	R	R	R	NR
Acetic Anhydride	NR	NR	NR	NR
Acetone	NR	NR	NR	NR
Acrylonitrile	NR	NR	NR	NR
Alcohol, Butyl	R	NR	NR	NR
Alcohol, Ethyl 10%	R	120	NR	NR
Alcohol, Ethyl 100%	NR	NR	NR	NR
Alcohol, Isopropyl 10%	R	150	NR	NR
Alcohol, Isopropyl 100%	R	NR	NR	NR
Alcohol, Methyl 10%	R	NR	NR	NR
Alcohol, Methyl 100%	NR	NR	NR	NR
Alcohol, Methyl Isobutyl	R	120	NR	NR
Alcohol, Secondary Butyl	R	150	NR	NR
Alum	R	120	R	R
Aluminum Chloride	R	120	R	NR
Aluminum Hydroxide 5%	R	120	NR	NR
Aluminum Nitrate	R	120	R	NR
Aluminum Potassium Sulfate	R	120	R	NR
Ammonia, Aqueous 0-10%	R	NR	NR	NR
Ammonia, Gas	R	NR	NR	NR
Ammonium Bicarbonate	R	120	R	NR
Ammonium Bisulfite	R	120	R	NR
Ammonium Carbonate 10%	R	120	NR	NR
Ammonium Citrate	R	120	R	NR
Ammonium Hydroxide 5%	R	120	NR	NR
Ammonium Hydroxide 10%	R	120	NR	NR
Ammonium Hydroxide 20%	R	NR	NR	NR
Ammonium Nitrate	R	R	R	R
Ammonium Persulfate	R	120	NR	NR
Ammonium Phosphate	R	120	NR	NR
Ammonium Sulfate	R	R	R	R
Arsenious Acid	R	R	R	NR
B				
Barium Acetate	R	R	NR	NR
Barium Carbonate	R	R	R	NR
Barium Chloride	R	R	R	120
Barium Hydroxide	R	120	NR	NR
Barium Sulfate	R	R	R	R
Barium Sulfide	R	R	NR	NR
Beer	R	120	R	NR
Benzene	NR	NR	NR	NR
5% Benzene in Kerosene	R	NR	NR	NR
Benzene Sulfonic Acid 30%	R	R	NR	NR

DURAGRATE® MOLDED GRATING

CHEMICAL ENVIRONMENT	FIBREBOLT® SYSTEM R.T. (≤ 100°F)	FIBREBOLT® SYSTEM 150°F	VINYL ESTER R.T. (≤ 100°F)	VINYL ESTER 160°F	PREMIUM ISOPHTHALIC POLYESTER R.T. (≤100°F)	PREMIUM ISOPHTHALIC POLYESTER 150°F
A						
Acetic Acid 0-25%	R	R	R	R	R	125
Acetic Acid 25-50%	R	R	R	R	R	NR
Acetic Anhydride	NR	NR	NR	NR	NR	NR
Acetone	NR	NR	NR	NR	NR	NR
Acrylonitrile	NR	NR	NR	NR	NR	NR
Alcohol, Butyl	R	NR	R	NR	NR	NR
Alcohol, Ethyl 10%	R	150	R	120	NR	NR
Alcohol, Ethyl 100%	NR	NR	NR	NR	NR	NR
Alcohol, Isopropyl 10%	R	150	R	150	NR	NR
Alcohol, Isopropyl 100%	R	NR	R	NR	NR	NR
Alcohol, Methyl 10%	R	NR	R	NR	NR	NR
Alcohol, Methyl 100%	NR	NR	NR	NR	NR	NR
Alcohol, Methyl Isobutyl	R	120	R	120	NR	NR
Alcohol, Secondary Butyl	R	150	R	150	NR	NR
Alum	R	120	R	120	NR	NR
Aluminum Chloride	R	120	R	120	R	NR
Aluminum Hydroxide 5%	R	120	R	120	NR	NR
Aluminum Nitrate	R	120	R	120	NR	NR
Aluminum Potassium Sulfate	R	120	R	120	NR	NR
Ammonia, Aqueous 0-10%	R	NR	R	NR	NR	NR
Ammonia, Gas	R	NR	R	NR	NR	NR
Ammonium Bicarbonate	R	120	R	120	R	NR
Ammonium Bisulfite	R	NR	R	120	R	NR
Ammonium Carbonate 10%	R	NR	R	120	NR	NR
Ammonium Citrate	R	120	R	120	R	NR
Ammonium Hydroxide 5%	R	NR	R	120	NR	NR
Ammonium Hydroxide 10%	R	NR	R	120	NR	NR
Ammonium Hydroxide 20%	R	NR	R	NR	NR	NR
Ammonium Nitrate	R	R	R	R	R	R
Ammonium Persulfate	R	NR	R	120	NR	NR
Ammonium Phosphate	R	120	R	120	NR	NR
Ammonium Sulfate	R	R	R	R	R	R
Arsenious Acid	R	R	R	R	R	NR
B						
Barium Acetate	R	120	R	R	NR	NR
Barium Carbonate	R	R	R	R	R	NR
Barium Chloride	R	R	R	R	R	120
Barium Hydroxide	R	NR	R	120	NR	NR
Barium Sulfate	R	R	R	R	R	R
Barium Sulfide	R	120	R	R	NR	NR
Beer	R	120	R	120	R	NR
Benzene	NR	NR	NR	NR	NR	NR
5% Benzene in Kerosene	R	NR	R	NR	NR	NR
Benzene Sulfonic Acid 30%	R	R	R	R	NR	NR

CHEMICAL ENVIRONMENT	VINYL ESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	VINYL ESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 160°F	POLYESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	POLYESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 150°F
B				
Benzoic Acid	R	R	R	NR
O-Benzoyl Benzoic Acid	R	R	NR	NR
Benzyl Alcohol	R	NR	NR	NR
Benzyl Chloride	NR	NR	NR	NR
Brass Plating Solution: 3% Copper Cyanide 6% Sodium Cyanide 1% Zinc Cyanide 3% Sodium Carbonate		R	120	NR
Butyl Acetate	NR	NR	NR	NR
Butylene Glycol	R	R	R	R
Butyric Acid 0-50%	R	R	R	NR
C				
Cadmium Chloride	R	R	R	NR
Cadmium Cyanide Plating Solution: 3% Cadmium Oxide, 6% Sodium Cyanide 1% Caustic Soda		R	120	NR
Calcium Bisulfite	R	R	R	R
Calcium Chlorate	R	R	R	R
Calcium Chloride	R	R	R	R
Calcium Hypochlorite	R	120	NR	NR
Calcium Nitrate	R	R	R	R
Calcium Sulfate	R	R	R	R
Calcium Sulfite	R	R	R	R
Caprylic Acid	R	R	R	NR
Carbon Dioxide	R	R	R	R
Carbon Disulfide	NR	NR	NR	NR
Carbon Monoxide	R	R	R	R
Carbon Tetrachloride	NR	NR	NR	NR
Carbonic Acid	R	R	R	NR
Carbon Methyl Cellulose	R	120	NR	NR
Castor Oil	R	R	R	R
Chlorinated Wax	R	R	NR	NR
Chlorine Dioxide/Air	R	R	NR	NR
Chlorine Dioxide, Wet Gas	R	R	NR	NR
Chlorine, Dry Gas	R	R	NR	NR
Chlorine, Wet Gas	R	R	NR	NR
Chlorine, Liquid	NR	NR	NR	NR
Chlorine, Swimming Pool (pH 7 to <8)	R	R	R	R
Chlorine, Water	R	120	NR	NR
Chloroacetic Acid 0-50%	R	NR	NR	NR
Chlorobenzene	NR	NR	NR	NR
Chloroform	NR	NR	NR	NR

CHEMICAL ENVIRONMENT	DURAGRATE® MOLDED GRATING					
	FIBREBOLT® SYSTEM R.T. (≤ 100°F)	FIBREBOLT® SYSTEM 150°F	VINYL ESTER R.T. (≤ 100°F)	VINYL ESTER 160°F	PREMIUM ISOPHTHALIC POLYESTER R.T. (≤100°F)	PREMIUM ISOPHTHALIC POLYESTER 150°F
B	Benzoic Acid	R	R	R	R	NR
	O-Benzoyl Benzoic Acid	R	R	R	NR	NR
	Benzyl Alcohol	R	NR	R	NR	NR
	Benzyl Chloride	NR	NR	NR	NR	NR
	Brass Plating Solution: 3% Copper Cyanide 6% Sodium Cyanide 1% Zinc Cyanide 3% Sodium Carbonate	R	R	R	NR	NR
	Butyl Acetate	NR	NR	NR	NR	NR
	Butylene Glycol	R	R	R	R	R
	Butyric Acid 0-50%	R	R	R	R	NR
C	Cadmium Chloride	R	R	R	R	NR
	Cadmium Cyanide Plating Solution: 3% Cadmium Oxide, 6% Sodium Cyanide 1% Caustic Soda	R	120	R	120	NR
	Calcium Bisulfite	R	R	R	R	R
	Calcium Chlorate	R	R	R	R	R
	Calcium Chloride	R	R	R	R	R
	Calcium Hypochlorite	C	C	R	120	NR
	Calcium Nitrate	R	R	R	R	R
	Calcium Sulfate	R	R	R	R	R
	Calcium Sulfite	R	R	R	R	R
	Caprylic Acid	R	R	R	R	NR
	Carbon Dioxide	R	R	R	R	R
	Carbon Disulfide	NR	NR	NR	NR	NR
	Carbon Monoxide	R	R	R	R	R
	Carbon Tetrachloride	NR	NR	NR	NR	NR
	Carbonic Acid	R	R	R	R	120
	Carbon Methyl Cellulose	R	120	R	120	NR
	Castor Oil	R	R	R	R	R
	Chlorinated Wax	R	120	R	R	NR
	Chlorine Dioxide/Air	R	120	R	R	NR
	Chlorine Dioxide, Wet Gas	R	NR	R	R	NR
	Chlorine, Dry Gas	R	NR	R	R	NR
	Chlorine, Wet Gas	R	NR	R	R	NR
	Chlorine, Liquid	NR	NR	NR	NR	NR
	Chlorine, Swimming Pool (pH 7 to <8)	R	NR	R	R	R
	Chlorine, Water	R	NR	R	NR	NR
	Chloroacetic Acid 0-50%	R	NR	R	NR	NR
	Chlorobenzene	NR	NR	NR	NR	NR
	Chloroform	NR	NR	NR	NR	NR

CHEMICAL ENVIRONMENT	VINYL ESTER COMPOSITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™	VINYL ESTER COMPOSITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™	POLYESTER COMPOSITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™	POLYESTER COMPOSITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™
R.T. (< 100°F)	160°F	R.T. (< 100°F)	150°F	
C				
Chlorosulfonic Acid	NR	NR	NR	NR
Chromic Acid	NR	NR	NR	NR
Chromium Sulfate	R	R	R	R
Citric Acid	R	R	R	R
Coconut Oil	R	R	R	NR
Copper Chloride	R	R	R	R
Copper Cyanide	R	R	R	NR
Copper Fluoride	R	R	NR	NR
Copper Nitrate	R	R	R	R
Copper Plating Solution:				
Copper Cyanide				
10.5% Copper	R	R	NR	NR
4% Copper Cyanide				
6% Rochelle Salts				
Copper Brite Plating:				
Caustic Cyanide	R	120	NR	NR
Copper Plating Solution:				
45% Copper Fluoborate	R	R	NR	NR
19% Copper Sulfate				
8% Sulfuric Acid				
Copper Matte Dipping Bath:				
30% Ferric Chloride	R	120	NR	NR
19% Hydrochloric Acid				
Copper Pickling Bath:				
10% Ferric Sulfate	R	R	NR	NR
10% Sulfuric Acid				
Copper Sulfate	R	R	R	R
Corn Oil	R	R	R	R
Corn Starch-Slurry	R	R	R	R
Corn Sugar	R	R	R	R
Cottonseed Oil	R	R	R	NR
Crude Oil, Sour	R	R	R	NR
Crude Oil, Sweet	R	R	R	NR
Cyclohexane	R	120	NR	NR
D				
Detergents, Sulfonated	R	R	R	NR
Di-Ammonium Phosphate	R	R	NR	NR
Dibromophenol	NR	NR	NR	NR
Dibutyl Ether	R	NR	NR	NR
Dichloro Benzene	NR	NR	NR	NR
Dichloroethylene	NR	NR	NR	NR
Diesel Fuel	R	R	R	NR
Diethylene Glycol	R	R	R	R
Dimethyl Phthalate	R	R	NR	NR

CHEMICAL ENVIRONMENT	DURAGRATE® MOLDED GRATING					
	FIBREBOLT® SYSTEM R.T. (≤ 100°F)	FIBREBOLT® SYSTEM 150°F	VINYL ESTER R.T. (≤ 100°F)	VINYL ESTER 160°F	PREMIUM ISOPHTHALIC POLYESTER R.T. (≤100°F)	PREMIUM ISOPHTHALIC POLYESTER 150°F
C Chlorosulfonic Acid	NR	NR	NR	NR	NR	NR
Chromic Acid	NR	NR	NR	NR	NR	NR
Chromium Sulfate	R	R	R	R	R	R
Citric Acid	R	R	R	R	R	R
Coconut Oil	R	R	R	R	R	NR
Copper Chloride	R	R	R	R	R	R
Copper Cyanide	R	R	R	R	R	NR
Copper Fluoride	NR	NR	R	R	NR	NR
Copper Nitrate	R	NR	R	R	R	R
Copper Plating Solution: Copper Cyanide	R	R	R	R	NR	NR
10.5% Copper						
4% Copper Cyanide						
6% Rochelle Salts						
Copper Bright Plating: Caustic Cyanide	R	120	R	120	NR	NR
Copper Plating Solution: 45% Copper Fluoborate	NR	NR	R	R	NR	NR
19% Copper Sulfate						
8% Sulfuric Acid						
Copper Matte Dipping Bath: 30% Ferric Chloride	R	R	R	R	NR	NR
19% Hydrochloric Acid						
Copper Pickling Bath: 10% Ferric Sulfate	R	R	R	R	NR	NR
10% Sulfuric Acid						
Copper Sulfate	R	R	R	R	R	R
Corn Oil	R	R	R	R	R	R
Corn Starch-Slurry	R	R	R	R	R	R
Corn Sugar	R	R	R	R	R	R
Cottonseed Oil	R	R	R	R	R	R
Crude Oil, Sour	R	R	R	R	R	NR
Crude Oil, Sweet	R	R	R	R	R	NR
Cyclohexane	R	120	R	120	NR	NR
D Detergents, Sulfonated	R	R	R	R	R	NR
Di-Ammonium Phosphate	R	R	R	R	NR	NR
Dibromophenol	NR	NR	NR	NR	NR	NR
Diethyl Ether	R	NR	R	NR	NR	NR
Dichloro Benzene	NR	NR	NR	NR	NR	NR
Dichloroethylene	NR	NR	NR	NR	NR	NR
Diesel Fuel	R	R	R	R	R	120
Diethylene Glycol	R	R	R	R	R	R
Dimethyl Phthalate	R	R	R	R	NR	NR

CHEMICAL ENVIRONMENT		VINYL ESTER COMPOSITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™	VINYL ESTER COMPOSITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™	POLYESTER COMPOSITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™	POLYESTER COMPOSITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™
D Diethyl Phthalate		R	R	NR	NR
Dipropylene Glycol		R	R	R	R
Dodecyl Alcohol		R	R	NR	NR
E Esters, Fatty Acids		R	R	R	R
Ethyl Acetate		NR	NR	NR	NR
Ethyl Benzene		NR	NR	NR	NR
Ethyl Ether		NR	NR	NR	NR
Ethylene Dichloride		NR	NR	NR	NR
Ethylene Glycol		R	R	R	R
F Fatty Acids		R	R	R	R
Ferric Chloride		R	R	R	R
Ferric Nitrate		R	R	R	R
Ferric Sulfate		R	R	R	R
Ferrous Chloride		R	R	R	R
Ferrous Nitrate		R	R	R	R
Ferrous Sulfate		R	R	R	R
8-8-8 Fertilizer		R	R	R	R
Fertilizer: Urea Ammonium Nitrate		R	120	NR	NR
Flue Gas		R	R	NR	NR
Formaldehyde		R	R	R	NR
Formic Acid 10%		R	R	R	NR
Fuel Oil		R	R	R	NR
G Gas, Natural		R	R	R	NR
Gasoline, Auto		R	R	R	NR
Gasoline, Aviation		R	R	R	NR
Gasoline, Ethyl		R	R	R	NR
Gasoline, Sour		R	R	R	NR
Glyconic Acid		R	R	R	NR
Glucose		R	R	R	R
Glycerine		R	R	R	R
Glycol, Propylene		R	R	R	R
Glycolic Acid 70%		R	R	R	NR
Gold Plating Solution: 63% Potassium Ferrocyanide 2% Potassium Gold Cyanide 8% Sodium Cyanide		R	R	NR	NR
H Heptane		R	R	R	NR
Hexane		R	R	R	NR
Hexalene Glycol		R	R	R	R

DURAGRATE® MOLDED GRATING

CHEMICAL ENVIRONMENT	FIBREBOLT® SYSTEM R.T. (≤ 100°F)	FIBREBOLT® SYSTEM 150°F	VINYL ESTER R.T. (≤ 100°F)	VINYL ESTER 160°F	PREMIUM ISOPHTHALIC POLYESTER R.T. (≤100°F)	PREMIUM ISOPHTHALIC POLYESTER 150°F
D Dioctyl Phthalate	R	R	R	R	NR	NR
Dipropylene Glycol	R	R	R	R	R	R
Dodecyl Alcohol	R	R	R	R	NR	NR
E Esters, Fatty Acids	R	R	R	R	R	R
Ethyl Acetate	NR	NR	NR	NR	NR	NR
Ethyl Benzene	NR	NR	NR	NR	NR	NR
Ethyl Ether	NR	NR	NR	NR	NR	NR
Ethylene Dichloride	NR	NR	NR	NR	NR	NR
Ethylene Glycol	R	R	R	R	R	R
F Fatty Acids	R	R	R	R	R	R
Ferric Chloride	R	R	R	R	R	R
Ferric Nitrate	R	R	R	R	R	R
Ferric Sulfate	R	R	R	R	R	R
Ferrous Chloride	R	R	R	R	R	R
Ferrous Nitrate	R	R	R	R	R	R
Ferrous Sulfate	R	R	R	R	R	R
8-8-8 Fertilizer	R	120	R	R	R	R
Fertilizer: Urea Ammonium Nitrate	R	120	R	120	NR	NR
Flue Gas	R	R	R	R	NR	NR
Formaldehyde	R	R	R	R	R	NR
Formic Acid 10%	C	C	R	R	R	NR
Fuel Oil	R	R	R	R	R	NR
G Gas, Natural	R	R	R	R	R	NR
Gasoline, Auto	R	R	R	120	R	NR
Gasoline, Aviation	R	R	R	120	R	NR
Gasoline, Ethyl	R	R	R	120	R	NR
Gasoline, Sour	R	R	R	120	R	NR
Glyconic Acid	R	R	R	R	R	NR
Glucose	R	R	R	R	R	R
Glycerine	R	R	R	R	R	R
Glycol, Propylene	R	R	R	R	R	R
Glycolic Acid 70%	R	R	R	R	R	NR
Gold Plating Solution: 63% Potassium Ferrocyanide 2% Potassium Gold Cyanide 8% Sodium Cyanide	R	R	R	R	R	NR
H Heptane	R	R	R	R	R	NR
Hexane	R	R	R	R	R	NR
Hexalene Glycol	R	R	R	R	R	R

CHEMICAL ENVIRONMENT	VINYL ESTER COMPOSOLITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	VINYL ESTER COMPOSOLITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 160°F	POLYESTER COMPOSOLITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	POLYESTER COMPOSOLITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 150°F
H Hydraulic Fluid	R	R	R	NR
Hydrobromic Acid 0-25%	R	R	R	NR
Hydrochloric Acid 0-37%	R	R	NR	NR
Hydrocyanic Acid	R	R	R	NR
Hydrofluoric Acid	NR	NR	NR	NR
Hydrofluorosilic Acid (Hydrofurosilicic Acid or Fluosilicic Acid)	NR	NR	NR	NR
Hydrogen Bromide, Wet Gas	R	R	NR	NR
Hydrogen Chloride, Dry Gas	R	R	NR	NR
Hydrogen Chloride, Wet Gas	R	120	NR	NR
Hydrogen Fluoride, Vapor	NR	NR	NR	NR
Hydrogen Peroxide 35%	R	120	NR	NR
Hydrogen Sulfide Dry	R	R	R	120
Hydrogen Sulfide, Aqueous	R	R	R	NR
Hydrosulfite Bleach	R	120	NR	NR
Hypochlorous Acid 0-10%	R	120	NR	NR
Iron Plating Solution: 45% FeCl ₂ ; 15% CaCl ₂ 20% FeSO ₄ ; 11% (NH ₄) ₂ SO ₄	R	R	NR	NR
Iron and Steel Cleaning Bath: 9% Hydrochloric, 23% Sulfuric	R	R	NR	NR
Isopropyl Amine	R	NR	NR	NR
Isopropyl Palmitate	R	R	R	R
J Jet Fuel	R	R	R	NR
K Kerosene	R	R	R	NR
L Lactic Acid	R	R	R	NR
Lauroyl Chloride	R	R	NR	NR
Lauric Acid	R	R	R	NR
Lead Acetate	R	R	R	NR
Lead Chloride	R	R	R	R
Lead Nitrate	R	R	R	R
Lead Plating Solution: 0.8% Fluoboric Acid 0.4% Boric Acid	R	120	NR	NR
Levulinic Acid	R	R	R	NR
Linseed Oil	R	R	NR	NR
Lithium Bromide	R	R	R	R
Lithium Sulfate	R	R	R	R

CHEMICAL ENVIRONMENT	DURAGRATE® MOLDED GRATING					
	FIBREBOLT® SYSTEM R.T. (≤ 100°F)	FIBREBOLT® SYSTEM 150°F	VINYL ESTER R.T. (≤ 100°F)	VINYL ESTER 160°F	PREMIUM ISOPHTHALIC POLYESTER R.T. (≤100°F)	PREMIUM ISOPHTHALIC POLYESTER 150°F
H Hydraulic Fluid	R	R	R	R	R	NR
Hydrobromic Acid 0-25%	NR	NR	R	R	R	NR
Hydrochloric Acid 0-37%	NR	NR	R	R	NR	NR
Hydrocyanic Acid	R	R	R	R	R	NR
Hydrofluoric Acid	NR	NR	NR	NR	NR	NR
Hydrofluorosilic Acid (Hydroflurosilicic Acid or Fluosilicic Acid)	NR	NR	NR	NR	NR	NR
Hydrogen Bromide, Wet Gas	NR	NR	R	R	NR	NR
Hydrogen Chloride, Dry Gas	NR	NR	R	R	NR	NR
Hydrogen Chloride, Wet Gas	NR	NR	R	120	NR	NR
Hydrogen Fluoride, Vapor	NR	NR	NR	NR	NR	NR
Hydrogen Peroxide 35%	C	C	R	120	R	120
Hydrogen Sulfide Dry	R	120	R	R	R	120
Hydrogen Sulfide, Aqueous	R	R	R	R	NR	NR
Hydrosulfite Bleach	C	C	R	120	NR	NR
Hypochlorous Acid 0-10%	C	C	R	120	NR	NR
Iron Plating Solution: 45% FeCl ₂ ; 15% CaCl ₂ 20% FeSO ₄ ; 11% (NH ₄) ₂ SO ₄	R	R	R	R	NR	NR
Iron and Steel Cleaning Bath: 9% Hydrochloric, 23% Sulfuric	C	C	R	R	NR	NR
Isopropyl Amine	R	NR	R	NR	NR	NR
Isopropyl Palmitate	R	R	R	R	R	R
J Jet Fuel	R	R	R	R	NR	NR
K Kerosene	R	R	R	R	R	120
L Lactic Acid	R	R	R	R	R	R
Lauroyl Chloride	R	R	R	R	NR	NR
Lauric Acid	R	R	R	R	NR	NR
Lead Acetate	R	R	R	R	R	R
Lead Chloride	R	R	R	R	R	R
Lead Nitrate	R	R	R	R	R	R
Lead Plating Solution: 0.8% Fluoboric Acid 0.4% Boric Acid	R	NR	R	120	NR	NR
Levulinic Acid	R	R	R	R	NR	NR
Linseed Oil	R	R	R	R	NR	NR
Lithium Bromide	R	R	R	R	R	R
Lithium Sulfate	R	R	R	R	R	R

CHEMICAL ENVIRONMENT	VINYL ESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	VINYL ESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 160°F	POLYESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	POLYESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 150°F
M				
Magnesium Bisulfite	R	R	NR	NR
Magnesium Chloride	R	R	R	R
Magnesium Hydroxide	R	140	NR	NR
Magnesium Nitrate	R	R	R	R
Magnesium Sulfate	R	R	R	R
Maleic Acid	R	R	NR	NR
Mercuric Chloride	R	R	R	R
Mercurous Chloride	R	R	R	R
Methanol 10% (see Alcohol, Methyl 10%)	R	NR	NR	NR
Methylene Chloride	NR	NR	NR	NR
Methyl Ethyl Ketone	NR	NR	NR	NR
Methyl Isobutyl Carbitol	NR	NR	NR	NR
Methyl Isobutyl Ketone	NR	NR	NR	NR
Methyl Styrene	NR	NR	NR	NR
Mineral Oils	R	R	R	R
Molybdenum Disulfide	R	R	NR	NR
Monochloric Acetic Acid	NR	NR	NR	NR
Monoethanolamine	NR	NR	NR	NR
Motor Oil	R	R	R	R
Myristic Acid	R	R	NR	NR
N				
Naphtha	R	R	R	R
Naphthalene	R	R	R	NR
Nickel Chloride	R	R	R	R
Nickel Nitrate	R	R	R	R
Nickel Plating: 8% Lead, 0.8% Fluoboric Acid 0.4% Boric Acid	R	R	NR	NR
Nickel Plating: 11% Nickel Sulfate 2% Nickel Chloride 1% Boric Acid	R	R	R	NR
Nickel Plating: 44% Nickel Sulfate 4% Ammonium Chloride 4% Boric Acid	R	R	R	NR
Nickel Sulfate	R	R	R	R
Nitric Acid 0-5%	R	R	R	NR
Nitric Acid 15%	R	120	NR	NR
Nitric Acid Fumes	NR	NR	NR	NR
Nitrobenzene	NR	NR	NR	NR

CHEMICAL ENVIRONMENT	DURAGRATE® MOLDED GRATING					
	FIBREBOLT® SYSTEM R.T. (≤ 100°F)	FIBREBOLT® SYSTEM 150°F	VINYL ESTER R.T. (≤ 100°F)	VINYL ESTER 160°F	PREMIUM ISOPHTHALIC POLYESTER R.T. (≤100°F)	PREMIUM ISOPHTHALIC POLYESTER 150°F
M Magnesium Bisulfite	R	R	R	R	NR	NR
Magnesium Chloride	R	R	R	R	R	R
Magnesium Hydroxide	R	140	R	140	NR	NR
Magnesium Nitrate	R	R	R	R	R	R
Magnesium Sulfate	R	R	R	R	R	R
Maleic Acid	R	R	R	R	NR	NR
Mercuric Chloride	R	R	R	R	R	R
Mercurous Chloride	R	R	R	R	R	R
Methanol 10% (see Alcohol, Methyl 10%)	R	NR	R	NR	NR	NR
Methylene Chloride	NR	NR	NR	NR	NR	NR
Methyl Ethyl Ketone	NR	NR	NR	NR	NR	NR
Methyl Isobutyl Carbitol	NR	NR	NR	NR	NR	NR
Methyl Isobutyl Ketone	NR	NR	NR	NR	NR	NR
Methyl Styrene	NR	NR	NR	NR	NR	NR
Mineral Oils	R	R	R	R	R	R
Molybdenum Disulfide	R	R	R	R	NR	NR
Monochloric Acetic Acid	NR	NR	NR	NR	NR	NR
Monoethanolamine	NR	NR	NR	NR	NR	NR
Motor Oil	R	R	R	R	R	R
Myristic Acid	R	R	R	R	NR	NR
N Naphtha	R	R	R	R	R	R
Naphthalene	R	R	R	R	R	NR
Nickel Chloride	R	R	R	R	R	R
Nickel Nitrate	R	R	R	R	R	R
Nickel Plating: 8% Lead, 0.8% Fluoboric Acid 0.4% Boric Acid	R	R	R	R	NR	NR
Nickel Plating: 11% Nickel Sulfate 2% Nickel Chloride 1% Boric Acid	R	R	R	R	R	NR
Nickel Plating: 44% Nickel Sulfate 4% Ammonium Chloride 4% Boric Acid	R	R	R	R	R	NR
Nickel Sulfate	R	R	R	R	R	R
Nitric Acid 0-5%	NR	NR	R	R	R	NR
Nitric Acid 15%	NR	NR	R	120	NR	NR
Nitric Acid Fumes	NR	NR	NR	NR	NR	NR
Nitrobenzene	NR	NR	NR	NR	NR	NR

CHEMICAL ENVIRONMENT	VINYL ESTER COMPOSOLITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	VINYL ESTER COMPOSOLITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 160°F	POLYESTER COMPOSOLITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	POLYESTER COMPOSOLITE® EXTREN® DURADEX® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 150°F
O	Octanoic Acid Oil, Sour Crude Oil, Sweet Crude Oleic Acid Oleum (Fuming Sulfuric) Olive Oil Oxalic Acid Ozone	R R R R NR R R NR	R R R R NR R R NR	R R R R NR R R NR
Peroxide Bleach:				
P	2% Sodium Peroxide 96% 0.025% Epsom Salts, 5% Sodium Silicate 42° Be, 1.4% Sulfuric Acid 66° Be	R	R	R
Phenols:				
	Phenol Phenol Sulfonic Acid Phosphoric Acid 85% Phosphoric Acid Fumes Phosphorous Pentoxide Phosphorous Trichloride Phthalic Acid	NR NR R R R NR R	NR NR R R R NR R	NR NR R R NR NR R
Pickling Acids:				
	Sulfuric and Hydrochloric	NR	NR	NR
Polyvinyl Compounds:				
	Picric Acid, Alcoholic Polyvinyl Acetate Latex Polyvinyl Alcohol Polyvinyl Chloride Latex (with 35 Parts DOP)	R R R R	R R R 120	R R R NR
Kalil Soda Ashes:				
	Potassium Aluminum Sulfate Potassium Bicarbonate Potassium Bromide Potassium Chloride Potassium Dichromate Potassium Ferricyanide Potassium Ferrocyanide Potassium Nitrate Potassium Permanganate Potassium Persulfate Potassium Sulfate Propionic Acid 1-50%	R R R R R R R R R R R R	R R R R R R R 140 R R R R	R NR NR R R R R NR R R R NR
Other Chemicals:				
	Propylene Glycol Pulp Paper Mill Effluent Pyridine	R R NR	R R NR	R R NR

DURAGRATE® MOLDED GRATING

CHEMICAL ENVIRONMENT	FIBREBOLT® SYSTEM R.T. (≤ 100°F)	FIBREBOLT® SYSTEM 150°F	VINYL ESTER R.T. (≤ 100°F)	VINYL ESTER 160°F	PREMIUM ISOPHTHALIC POLYESTER R.T. (≤100°F)	PREMIUM ISOPHTHALIC POLYESTER 150°F
O Octanoic Acid	R	R	R	R	R	NR
Oil, Sour Crude	R	R	R	R	R	R
Oil, Sweet Crude	R	R	R	R	R	R
Oleic Acid	R	R	R	R	R	R
Oleum (Fuming Sulfuric)	NR	NR	NR	NR	NR	NR
Olive Oil	R	R	R	R	R	R
Oxalic Acid	R	R	R	R	R	R
Ozone	NR	NR	NR	NR	NR	NR
Peroxide Bleach:						
P 2% Sodium Peroxide 96%	R	R	R	R	R	R
0.025% Epsom Salts,						
5% Sodium Silicate 42° Be,						
1.4% Sulfuric Acid 66° Be						
Phenol	NR	NR	NR	NR	NR	NR
Phenol Sulfonic Acid	NR	NR	NR	NR	NR	NR
Phosphoric Acid 85%	C	C	R	R	R	R
Phosphoric Acid Fumes	C	C	R	R	R	R
Phosphorous Pentoxide	C	C	R	R	R	NR
Phosphorous Trichloride	NR	NR	NR	NR	NR	NR
Phthalic Acid	R	R	R	R	R	R
Pickling Acids:						
Sulfuric and Hydrochloric	NR	NR	NR	NR	NR	NR
Picric Acid, Alcoholic	NR	NR	R	R	R	NR
Polyvinyl Acetate Latex	R	R	R	R	R	NR
Polyvinyl Alcohol	R	NR	R	NR	R	NR
Polyvinyl Chloride Latex (with 35 Parts DOP)	R	120	R	120	NR	NR
Potassium Aluminum Sulfate	R	R	R	R	R	R
Potassium Bicarbonate	R	R	R	R	R	NR
Potassium Bromide	R	R	R	R	NR	NR
Potassium Chloride	R	R	R	R	R	R
Potassium Dichromate	R	120	R	140	NR	NR
Potassium Ferricyanide	R	R	R	R	R	R
Potassium Ferrocyanide	R	R	R	R	R	R
Potassium Nitrate	R	R	R	R	R	R
Potassium Permanganate	R	140	R	140	NR	NR
Potassium Persulfate	R	R	R	R	R	NR
Potassium Sulfate	R	R	R	R	R	R
Propionic Acid 1-50%	R	120	R	120	NR	NR
Propylene Glycol	R	R	R	R	R	R
Pulp Paper Mill Effluent	R	R	R	R	NR	NR
Pyridine	NR	NR	NR	NR	NR	NR

CHEMICAL ENVIRONMENT	VINYL ESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	VINYL ESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 160°F	POLYESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	POLYESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 150°F
S Salicylic Acid	R	140	NR	NR
Sebacic Acid	R	R	NR	NR
Selenious Acid	R	R	NR	NR
Silver Nitrate	R	R	R	R
Silver Plating Solution: 4% Silver Cyanide				
7% Potassium Cyanide	R	R	NR	NR
5% Sodium Cyanide				
2% Potassium Carbonate				
Sodium Acetate	R	R	R	NR
Sodium Benzoate	R	R	R	NR
Sodium Bicarbonate	R	R	NR	NR
Sodium Bifluoride	R	120	R	NR
Sodium Bisulfate	R	R	R	R
Sodium Bisulfite	R	R	R	R
Sodium Bromate	R	140	R	R
Sodium Bromide	R	R	R	R
Sodium Chlorate	R	R	R	NR
Sodium Chloride	R	R	R	R
Sodium Chlorite 25%	R	R	R	NR
Sodium Chromate	R	R	NR	NR
Sodium Cyanide	R	R	R	NR
Sodium Dichromate	R	R	NR	NR
Sodium Di-Phosphate	R	R	R	R
Sodium Ferricyanide	R	R	R	R
Sodium Fluoride	R	120	NR	NR
Sodium Fluoro Silicate	R	120	NR	NR
Sodium Hexametaphosphates	R	NR	NR	NR
Sodium Hydroxide 0-5%	R	150	NR	NR
Sodium Hydroxide 5-50%	R	120	NR	NR
Sodium Hydrosulfide	R	R	R	NR
Sodium Hypochlorite (5% bleach)	R	120	NR	NR
Sodium Hypochlorite 5-15% Commercial Grade	R	NR	NR	NR
Sodium Lauryl Sulfate	R	R	R	R
Sodium Mono-Phosphate	R	R	R	R
Sodium Nitrate	R	R	R	R
Sodium Silicate	R	R	R	R
Sodium Sulfate	R	R	R	R
Sodium Sulfide	R	R	R	R
Sodium Sulfite	R	R	R	NR
Sodium Tetra Borate	R	R	R	R
Sodium Thiocyanate	R	R	NR	NR
Sodium Thiosulfate	R	R	R	NR

CHEMICAL ENVIRONMENT	DURAGRATE® MOLDED GRATING					
	FIBREBOLT® SYSTEM R.T. (≤ 100°F)	FIBREBOLT® SYSTEM 150°F	VINYL ESTER R.T. (≤ 100°F)	VINYL ESTER 160°F	PREMIUM ISOPHTHALIC POLYESTER R.T. (≤100°F)	PREMIUM ISOPHTHALIC POLYESTER 150°F
S Salicylic Acid	R	140	R	140	NR	NR
Sebacic Acid	R	R	R	R	NR	NR
Selenious Acid	R	R	R	R	NR	NR
Silver Nitrate	R	R	R	R	R	R
Silver Plating Solution: 4% Silver Cyanide 7% Potassium Cyanide 5% Sodium Cyanide 2% Potassium Carbonate	R	R	R	R	NR	NR
Sodium Acetate	R	R	R	R	R	NR
Sodium Benzoate	R	R	R	R	R	NR
Sodium Bicarbonate	R	R	R	R	NR	NR
Sodium Bifluoride	R	120	R	120	R	NR
Sodium Bisulfate	R	R	R	R	R	R
Sodium Bisulfite	R	R	R	R	R	R
Sodium Bromate	R	140	R	140	R	NR
Sodium Bromide	R	R	R	R	R	R
Sodium Chlorate	R	R	R	R	R	NR
Sodium Chloride	R	R	R	R	R	R
Sodium Chlorite 25%	R	R	R	R	R	NR
Sodium Chromate	R	R	R	R	NR	NR
Sodium Cyanide	R	R	R	R	R	NR
Sodium Dichromate	R	R	R	R	NR	NR
Sodium Di-Phosphate	R	R	R	R	R	R
Sodium Ferricyanide	R	R	R	R	R	R
Sodium Fluoride	R	120	R	120	NR	NR
Sodium Fluoro Silicate	R	120	R	120	NR	NR
Sodium Hexametaphosphates	R	NR	R	NR	NR	NR
Sodium Hydroxide 0-5%	R	150	R	150	NR	NR
Sodium Hydroxide 5-50%	R	120	R	120	NR	NR
Sodium Hydrosulfide	R	R	R	R	R	NR
Sodium Hypochlorite (5% bleach)	R	120	R	120	NR	NR
Sodium Hypochlorite 5-15% Commercial Grade	R	NR	R	NR	NR	NR
Sodium Lauryl Sulfate	R	R	R	R	R	R
Sodium Mono-Phosphate	R	R	R	R	R	R
Sodium Nitrate	R	R	R	R	R	R
Sodium Silicate	R	R	R	R	R	R
Sodium Sulfate	R	R	R	R	R	R
Sodium Sulfide	R	R	R	R	R	R
Sodium Sulfite	R	R	R	R	R	NR
Sodium Tetra Borate	R	R	R	R	R	R
Sodium Thiocyanate	R	R	R	R	NR	NR
Sodium Thiosulfate	R	R	R	R	R	NR

CHEMICAL ENVIRONMENT	VINYL ESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	VINYL ESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 160°F	POLYESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	POLYESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 150°F
S				
Sodium Tripolyphosphate	R	R	R	NR
Sodium Xylene Sulfonate	R	R	R	NR
Soya Oil	R	R	R	R
Stannic Chloride	R	R	R	R
Stannous Chloride	R	R	R	R
Stearic Acid	R	R	R	R
Styrene	NR	NR	NR	NR
Sugar, Beet and Cane Liquor	R	R	R	NR
Sugar, Sucrose	R	R	R	R
Sulfamic Acid	R	R	R	NR
Sulfanilic Acid 50%	R	R	NR	NR
Sulfated Detergents	R	R	R	NR
Sulfur Dioxide, Dry or Wet	R	R	NR	NR
Sulfur, Trioxide/Air	R	R	NR	NR
Sulfuric Acid 0-30%	R	R	R	NR
Sulfuric Acid 30-50%	R	R	NR	NR
Sulfuric Acid 50-70%	R	NR	NR	NR
Sulfurous Acid 10%	R	NR	NR	NR
Superphosphoric Acid (76% P ₂ O ₅)	R	R	NR	NR
T				
Tall Oil	R	150	R	NR
Tannic Acid	R	120	R	NR
Tartaric Acid	R	R	R	R
Thionyl Chloride	NR	NR	NR	NR
Tin Plating:				
18% Stannous Fluoborate				
7% Tin	R	120	NR	NR
9% Fluoboric Acid				
2% Boric Acid				
Toluene	NR	NR	NR	NR
Toluene Sulfonic Acid	R	R	NR	NR
Transformer Oils:				
Mineral Oil Types	R	R	R	R
Chloro-Phenyl Types	NR	NR	NR	NR
Trichloro Acetic Acid	NR	NR	NR	NR
Trichlorethylene	NR	NR	NR	NR
Trichloropenol	NR	NR	NR	NR
Tricresyl Phosphate	R	120	NR	NR
Tridecylbenzene Sulfonate	R	R	NR	NR
Trisodium Phosphate	R	R	R	NR
Turpentine	R	NR	NR	NR

CHEMICAL ENVIRONMENT	DURAGRATE® MOLDED GRATING					
	FIBREBOLT® SYSTEM R.T. (≤ 100°F)	FIBREBOLT® SYSTEM 150°F	VINYL ESTER R.T. (≤ 100°F)	VINYL ESTER 160°F	PREMIUM ISOPHTHALIC POLYESTER R.T. (≤100°F)	PREMIUM ISOPHTHALIC POLYESTER 150°F
S Sodium Tripolyphosphate	R	R	R	R	R	NR
Sodium Xylene Sulfonate	R	R	R	R	R	NR
Soya Oil	R	R	R	R	R	R
Stannic Chloride	R	R	R	R	R	R
Stannous Chloride	R	R	R	R	R	R
Stearic Acid	R	R	R	R	R	R
Styrene	NR	NR	NR	NR	NR	NR
Sugar, Beet and Cane Liquor	R	R	R	R	R	NR
Sugar, Sucrose	R	R	R	R	R	R
Sulfamic Acid	R	R	R	R	R	NR
Sulfanilic Acid 50%	R	R	R	R	NR	NR
Sulfated Detergents	R	R	R	R	R	NR
Sulfur Dioxide, Dry or Wet	R	R	R	R	NR	NR
Sulfur, Trioxide/Air	R	R	R	R	NR	NR
Sulfuric Acid 0-30%	R	C	R	R	R	R
Sulfuric Acid 30-50%	C	C	R	R	NR	NR
Sulfuric Acid 50-70%	C	C	R	NR	NR	NR
Sulfurous Acid 10%	R	NR	R	NR	NR	NR
Superphosphoric Acid (76% P ₂ O ₅)	C	C	R	R	NR	NR
T Tall Oil	R	140	R	150	R	NR
Tannic Acid	R	150	R	120	R	NR
Tartaric Acid	R	R	R	R	R	R
Thionyl Chloride	NR	NR	NR	NR	NR	NR
Tin Plating:						
18% Stannous Fluoborate						
7% Tin	R	R	R	120	NR	NR
9% Fluoboric Acid						
2% Boric Acid						
Toluene	NR	NR	NR	NR	NR	NR
Toluene Sulfonic Acid	R	R	R	R	NR	NR
Transformer Oils:						
Mineral Oil Types	C	C	R	R	R	R
Chloro-Phenyl Types	NR	NR	NR	NR	NR	NR
Trichloro Acetic Acid	C	C	NR	NR	NR	NR
Trichlorethylene	NR	NR	NR	NR	NR	NR
Trichloropenol	NR	NR	NR	NR	NR	NR
Tricresyl Phosphate	R	120	R	120	NR	NR
Tridecylbenzene Sulfonate	R	R	R	R	R	NR
Trisodium Phosphate	R	R	R	R	R	NR
Turpentine	R	NR	R	NR	NR	NR

CHEMICAL ENVIRONMENT		VINYL ESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	VINYL ESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 160°F	POLYESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ R.T. (< 100°F)	POLYESTER COMPOSOLITE® EXTREN® DURADEK® DURAGRID® DURASHIELD® SAFPLANK® SAFPLATE® SAFRAIL™ 150°F
U	Urea	R	140	R	NR
V	Vegetable Oils	R	R	R	R
	Vinegar	R	R	R	R
	Vinyl Acetate	NR	NR	NR	NR
W	Water:				
	Deionized	R	R	R	R
	Demineralized	R	R	R	R
	Distilled	R	R	R	R
	Fresh	R	R	R	R
	Salt	R	R	R	R
	Sea	R	R	R	R
	White Liquor (Pulp Mill)	R	R	NR	NR
X	Xylene	NR	NR	NR	NR
Z	Zinc Chlorate	R	R	R	R
	Zinc Nitrate	R	R	R	R
	Zinc Plating Solution: 9% Zinc Cyanide 4% Sodium Cyanide 9% Sodium Hydroxide	R	120	NR	NR
	Zinc Plating Solution: 49% Zinc Fluoborate 5% Ammonium Chloride 6% Ammonium Fluoborate	R	120	NR	NR
	Zinc Sulfate	R	R	R	R

DURAGRATE® MOLDED GRATING

CHEMICAL ENVIRONMENT	FIBREBOLT® SYSTEM R.T. (≤ 100°F)	FIBREBOLT® SYSTEM 150°F	VINYL ESTER R.T. (≤ 100°F)	VINYL ESTER 160°F	PREMIUM ISOPHTHALIC POLYESTER R.T. (≤100°F)	PREMIUM ISOPHTHALIC POLYESTER 150°F
U Urea	R	NR	R	140	R	NR
V Vegetable Oils	R	R	R	R	R	R
Vinegar	R	R	R	R	R	R
Vinyl Acetate	NR	NR	NR	NR	NR	NR
W Water:						
Deionized	R	R	R	R	R	R
Demineralized	R	R	R	R	R	R
Distilled	R	R	R	R	R	R
Fresh	R	R	R	R	R	R
Salt	R	R	R	R	R	R
Sea	R	R	R	R	R	R
White Liquor (Pulp Mill)	R	R	R	R	NR	NR
X Xylene	NR	NR	NR	NR	NR	NR
Z Zinc Chlorate	R	R	R	R	R	R
Zinc Nitrate	R	R	R	R	R	R
Zinc Plating Solution: 9% Zinc Cyanide 4% Sodium Cyanide 9% Sodium Hydroxide	R	120	R	120	NR	NR
Zinc Plating Solution: 49% Zinc Fluoborate 5% Ammonium Chloride 6% Ammonium Fluoborate	R	R	R	120	NR	NR
Zinc Sulfate	R	R	R	R	R	R



ISO-9001:2008 Quality Certified and ISO-14001:2004 Environmentally Certified Manufacturing Plants

Chatfield Location

1610 Highway 52 South
Chatfield, Minnesota 55923-9799 USA

Phone: +1 507.867.3479
Fax: +1 507.867.4031

Corporate Offices | Bristol Location

400 Commonwealth Ave., P. O. Box 580
Bristol, Virginia 24203-0580 USA
info@strongwell.com
Phone: +1 276.645.8000
Fax: +1 276.645.8132

www.strongwell.com

Highlands Location

26770 Newbanks Road
Abingdon, VA 24210 USA

Phone: +1 276.645.8000
Fax: +1 276.645.8132